

TGP1200, 1500, 3000, 5000, 6000 and 8000 Thermal Gap Filler Pad

BENEFITS AND FEATURES

- High thermal performance
- Ultra-high compressibility for low stress applications
- Excellent surface wetting for low contact resistance
- High reliability
- Electrically insulating

OVERVIEW

Honeywell TGP series Thermal Gap Filler Pads provide high thermal performance with ease of use across multitude of applications. Its ultra-high compressibility enables low stress and excellent conformity to mating surfaces. It is designed to minimize thermal resistance at interfaces and maintain excellent performance through reliability testing. TGP series products are naturally tacky and require no additional adhesive which might weaken thermal performance. Products are available in thickness range from 0.5mm to 5.0mm.

TYPICAL APPLICATIONS

- Consumer electronics
- Telecommunications & network servers
- Automotive electronics
- Power devices & modules
- Semiconductors logics & memory

STORAGE & USE

Shelf life 12 months at 0 ~ 35°C
and <65% RH

Product Name	TGP 1200	TGP 1500	TGP 3000	TGP 5000	TGP 6000	TGP 8000	Test Method
Color	Blue	Grey	Yellow	Blue	Grey	Grey	Visual
Thickness (mm)*	0.5-5	0.5-5	0.5-5	0.5-5	0.5-5	0.5-5	ASTM D374
Thermal Conductivity (W/m·K)	1.2	1.5	3.0	5.0	6.0	8.0	ASTM D5470
Thermal Impedance (°C ·in ² /W) (1mm@10psi) (Typical Value)	1.19	0.85	0.51	0.3	0.25	0.2	ASTM D5470
Hardness (Shore00)	40	40	40	45	40	30	ASTM D2240
Density (g/cc)	1.75	1.8	3.1	3.3	3.3	3.4	ASTM D792
Dielectric Constant@1MHz	4.5	5.5	6.8	5.5	8.5	8.3	ASTM D150
Volume Resistivity (ohm·cm)	4x10 ¹²	2x10 ¹³	5x10 ¹³	9x10 ¹³	4x10 ¹⁵	7x10 ¹⁵	ASTM D257
Flammability Rating	V-0	V-0	V-0	V-0	V-0	V-0	UL94

* Thickness range: 0.5-5.0mm with 0.25mm incremental
There is one layer of fiberglass for the pad less than 1mm
Thickness Tolerance: >1mm, ±10%
0.5-1mm, ±0.1mm
<0.5mm, ±0.05mm
Please check thickness availability before order

Honeywell Electronic Materials

USA: 1-509-252-2102
Mainland China: 400-840-2233
Germany: 49-5137-999-9199
Japan: 81-3-6730-7092
Korea: 82-2-3483-5076
Singapore: 65-6580-3593
Taiwan: 886-3-6580300 ext.312
www.electronicmaterials.com

Although all statements and information contained herein are believed to be accurate and reliable, they are presented without guarantee or warranty of any kind, express or implied. Information provided herein does not relieve the user from the responsibility of carrying out its own tests and experiments, and the user assumes all risks and liability for use of the information and results obtained. Statements or suggestions concerning the use of materials and processes are made without representation or warranty that any such use is free of patent infringement and are not recommendations to infringe any patent. The user should not assume that all toxicity data and safety measures are indicated herein or that other measures may not be required.